



TUFboard DECK BELLUS Collection Technical Specifications

PROPERTY	TEST METHOD	UNIT	TYPICAL PROPERTY
Material			PVC and Proprietary Components
Weight		lb/ft	1.69
Modulus of Elasticity (MOE)	ASTM D6109	psi	250,000
Modulus of Rupture (MOR)	ASTM D6109	psi	4,900
Coefficient of Friction (COF)	ASTM D2394		0.62 (DRY); 0.64 (WET)
Coefficient of Linear Expansion	ASTM D696	1/°F	2.98 X 10-5
Screw Pull Through	ASTM D1037	lbf	107 (#7 deck screw)
Allowable Wind Uplift Capacity (by Hidden Fasteners)	ASTM E330 / D7032	lb/ft ²	172 (Grooved, Tiger Claw TC-G) 189 (Square, Tiger Claw TC-3S)
Deck Board Span Rating	AC 174	in lb/ft ²	Max. Span: 16 Allowable Capacity: 100
Maximum Stair Thread Span	AC 174	in	12
Stair Tread Load Max. design load deflection	ASTM D7032	in	Passed, Deflection < 1/8"
Moisture Effect	ASTM D7032		Passed, Effect <10%
UV Resistance	ASTM D7032		Passed, Effect <10%
Freeze-Thaw Resistance	ASTM D7032		Passed, Effect <10%
Termite and Decay Resistance	ASTM D7032		Passed
Creep Relaxation	ASTM D7032		Passed, 100% recovery
Duration of Load	ASTM D7031		Passed, No Failure and Creep

The information contained herein is true and accurate to the best of our knowledge. All recommendations and suggestions are made without guarantees. This information is to be used by individuals with technical skill at their own discretion and risk. Because conditions of use are beyond our control, World-Pak Division, Inteplast Group, Ltd. makes no warranties, expressed or implied, and assumes no liability in connection with the use of this information.

Note: The above properties may vary slightly due to production variation.

PVC SHEET BUSINESS UNIT

9 Peach Tree Hill Road
Livingston, NJ 07039
Tel: 877-977-2386
Fax: 800-889-8807

